

TO. : BLUME

NO. : A240829



APPROVAL SHEET

MULTILAYER CERAMIC CAPACITOR

Automotive Grade, Soft Termination Type

(AEC-Q200 Qualified)

Approved by customer : (signing or stamping here)

SAMWHA CAPACITOR CO., LTD.		
Prepared by	Checked by	Approved by
		

2024. 08. 29.



SAMWHA CAPACITOR CO., LTD.

Address : 227,GYEONGGIDONG-RO, NAMSA-EUP, CHEOIN-GU, YONGIN-SI, GYEONGGI-DO, KOREA

Contact : TEL 82-31-332-6441 , FAX 82-31-332-7661

Home page : www.samwha.com

< SPECIFICATION SUMMARY >

SAMWHA Part no.	CQ2012X7R473K101ARE		
Type	MLCC for Automotive Application		
Items	Specification	Unit	Test Conditions
Capacitance	47	nF	Testing Frequency : 1 ±0.1 kHz Testing Voltage : 1 ±0.2 Vrms Should be measured at 25℃.
Capacitance Tolerance	± 10	%	
Dissipation Factor	Max. 2.5	%	
Insulation Resistance	Min. 10,000	MΩ	Should be measured with a DC voltage not exceeding rated voltage at 25℃ for 2 minutes of charging.
Chip Size	2.00 -0.20/+0.30	L (mm)	Capacitance Tolerance Code ----- page 1/9 Chip size ----- page 2/9 Characteristics & Test Method ----- page 3/9~6/9
	1.25 ±0.20	W (mm)	
	1.25 ±0.20	T (mm)	

Contents

General Description	1/9
Specifications and Test Methods	3/9
Packing	7/9
Caution	8/9
Note	9/9

Enactment : Feb. 1, 2010	STANDARD	NO	SW - Q - 01A
	MULTILAYER CERAMIC CAPACITOR Automotive Grade, Soft Termination Type	Page	1 / 9

*Caution : Reflow soldering only

1. General Code

(1) Type Designation

CQ **2012** **X7R** **473** **K** **101** **A** **R** **E**
 (1) (2) (3) (4) (5) (6) (7) (8) (9)

1) Multilayer Ceramic Capacitor (Automotive Grade)

2) Size Code :

This is expressed in tens of a millimeter.

The first two digits are the length, The last two digits are width.

3) Temperature Coefficient Code

Classification	Code	Temperature Range	Capacitance Tolerance
Class I	C0G	-55 to +125℃	±30 ppm/℃
Class II	X7R	-55 to +125℃	±15%
	X7S	-55 to +125℃	±22%
	X7T	-55 to +125℃	+22% ~ -33%
	X6S	-55 to +105℃	±22%

4) Capacitance Code(Pico farads) :

The nominal Capacitance Value in pF is expressed by three digit numbers.

The first two digits represents significant figures and the last digit denotes the number of zero

ex) 104 = 100000 pF

R denotes decimal

8R2 = 8.2 pF

5) Capacitance Tolerance Code

Code	Tolerance
B	± 0.1 pF
C	± 0.25 pF
D	± 0.5 pF
F	± 1.0 %

Code	Tolerance
G	± 2.0 %
J	± 5 %
K	± 10 %
M	± 20 %

6) Voltage Code

Code	6R3	100	160	250	350	500	101	201	251	501	631	102	202	302
Rated Voltage	DC 6.3V	DC 10V	DC 16V	DC 25V	DC 35V	DC 50V	DC 100V	DC 200V	DC 250V	DC 500V	DC 630V	DC 1KV	DC 2KV	DC 3KV

7) Termination Code

N : Nickel-Tin Plate

A : Nickel-Tin Plate -> Soft Termination Type

8) Packing Code

R : 7" Reel Type, L : 13" Reel Type, B : Bulk Type

9) Thickness option


Thickness (mm)		Code	Thickness (mm)		Code
t	Tol(±)		t	Tol(±)	
0.50	0.10	Blank	1.35	0.20	H
0.60	0.10	A	1.60	0.30	I
0.80	0.15	B	1.80	0.30	J
0.85	0.15	B	2.00	0.30	K
1.00	0.15	E	2.50	0.30	L
1.10	0.15	E	2.80	0.30	M
1.15	0.20	E	3.20	0.40	N
1.25	0.20	E	5.00	0.50	O
1.30	0.20	E			

2. Temperature Characteristics

See Page 6/9 (No.21)

3. Constructions and Dimensions


(1) Dimensions




Size Code	EIA Code	Dimension						
		Length			Width		T1(min.)	G(min.)
		L	Tol(-)	Tol(+)	W	Tol(±)		
1005	0402	1.00	0.05	0.10	0.50	0.10	0.15	0.30
1608	0603	1.60	0.15	0.20	0.80	0.15	0.20	0.50
2012	0805	2.00	0.20	0.30	1.25	0.20	0.20	0.70
3216	1206	3.20	0.50	0.50	1.60	0.30	0.30	1.20
3225	1210	3.20	0.50	0.50	2.50	0.30	0.30	1.00
4520	1808	4.50	0.50	0.50	2.00	0.30	0.30	1.00
4532	1812	4.50	0.50	0.50	3.20	0.40	0.30	2.20
5750	2220	5.70	0.30	0.70	5.00	0.50	0.30	3.20

(Unit : mm)

(2) Construction of Termination



Specifications and Test Methods (For Automotive Applications)

No.	AEC-Q200 Test Item		Specification		Test Methods and Conditions															
			Class I	Class II																
1	Pre-and Post-Stress Electrical Test		-																	
2	High Temperature Exposure	Appearance	No defects which may affect performance		Temperature : Max. operating temperature±3℃ Maintenance Time : 1000+48/-0 hrs Let sit for 24±2 hours at room temperature, then measure.															
		Capacitance Change	Within ±2.5% or ±0.25pF (Whichever is larger)	Within ±10.0% (*Within ±12.5%)																
		Q/D.F.	30pF min.: Q≥1000 30pF max.: Q≥400+20×C C: Nominal Capacitance (pF)	Rated Voltage 16V min.: 0.05 max. 10V: 0.075 max. *0.2 max.																
		I.R.	More than 10,000MΩ or 500Ω·F (*50Ω·F) (Whichever is smaller)																	
3	Temperature Cycling	Appearance	No defects which may affect performance		Perform the 1000 cycles according to the four heat treatments listed in the following table. Let sit for 24±2 hours at room temperature, then measure.															
		Capacitance Change	Within ±2.5% or ±0.25pF (Whichever is larger)	Within ±10.0%																
		Q/D.F.	30pF min.:Q≥1000 30pF max.:Q≥400+20×C C: Nominal Capacitance (pF)	Rated Voltage 16V min.: 0.05 max. 10V: 0.075 max. *0.2 max.	<table><tr><td>Step</td><td>1</td><td>2</td><td>3</td><td>4</td></tr><tr><td>Temp.(℃)</td><td>-55+0/-3</td><td>25±2</td><td>125+3/-0</td><td>25±2</td></tr><tr><td>Time(min)</td><td>15±3</td><td>1</td><td>15±3</td><td>1</td></tr></table>	Step	1	2	3	4	Temp.(℃)	-55+0/-3	25±2	125+3/-0	25±2	Time(min)	15±3	1	15±3	1
		Step	1	2	3	4														
Temp.(℃)	-55+0/-3	25±2	125+3/-0	25±2																
Time(min)	15±3	1	15±3	1																
I.R.	More than 10,000MΩ or 500Ω·F (*50Ω·F) (Whichever is smaller)		Initial measurement Perform the initial measurement according to Note 1 for Class II.																	
4	Destructive Physical Analysis		No defects or abnormalities		Per EIA-469															
5	Moisture Resistance	Appearance	No defects which may affect performance		Temperature : 25~65℃, Humidity : 80~98% Cycle Time : 24 hrs/cycle, 10 cycles Let sit for 24±2 hours at room temperature, then measure. 															
		Capacitance Change	Within ±3.0% or±0.30pF (Whichever is larger)	Within ±12.5%																
		Q/D.F.	30pF min.: Q≥350 10pF min. and 30pF max.: Q≥275+5/2×C 10pF max.: Q≥200+10×C C: Nominal Capacitance (pF)	Rated Voltage 16V min.: 0.05 max. 10V: 0.075 max. *0.2 max.																
		I.R.	More than 10,000MΩ or 500Ω·F (*50Ω·F) (Whichever is smaller)																	
6	Humidity Bias	Appearance	No defects which may affect performance		Temperature : 85±3℃ Humidity : 80~85% Applied Voltage : Rated Voltage and 1.3+0.2/-0V Maintenance Time : 1000+48/-0 hrs Let sit for 24±2 hours at room temperature, then measure. The charge/discharge current is less than 50mA.															
		Capacitance Change	Within ±3.0% or ±0.30pF (Whichever is larger)	Within ±12.5%																
		Q/D.F.	30pF min.: Q≥200 30pF max.: Q≥100+10/3×C C: Nominal Capacitance (pF)	Rated Voltage 16V min.: 0.05 max. 10V: 0.075 max. *0.2 max.																
		I.R.	More than 1,000MΩ or 50Ω·F (*5Ω·F) (Whichever is smaller)																	
7	High Temperature Operating Life	Appearance	No defects which may affect performance		Temperature : Max. operating temperature±3℃ Applied Voltage : Rated Voltage × 200% (*150%) Maintenance Time : 1000+48/-0 hrs Let sit for 24±2 hours at room temperature, then measure. The charge/discharge current is less than 50mA. Initial Measurement for Class II Applied 200% of the rated voltage for one hour at 125±3℃. Remove and let sit for 24±2 hours at room temperature, then measure.															
		Capacitance Change	Within ±3.0% or ±0.30pF (Whichever is larger)	Within ±12.5%																
		Q/D.F.	30pF min.:Q≥350 10pF min. and 30pF max.: Q≥275+5/2×C 10pF max.: Q≥200+10×C C: Nominal Capacitance (pF)	Rated Voltage 16V min.: 0.05 max. 10V: 0.075 max. *0.2 max.																
		I.R.	More than 1,000MΩ or 50Ω·F (*5Ω·F) (Whichever is smaller)																	

Specifications and Test Methods (For Automotive Application)

No.	AEC-Q200 Test Item	Specification		Test Methods and Conditions
		Class I	Class II	
8	External Visual	No defects or abnormalities		Visual inspection
9	Physical Dimension	Within the specified dimensions		Using calipers
10	Resistance to Solvents	Appearance	No defects which may affect performance	
		Capacitance Change	Within the specified tolerance	
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.
		I.R.	More than 10,000M Ω or 500 Ω -F (*50 Ω -F) (Whichever is smaller)	
11	Mechanical Shock	Appearance	No defects which may affect performance	
		Capacitance Change	Within the specified tolerance	
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.
		I.R.	More than 10,000M Ω or 500 Ω -F (*50 Ω -F) (Whichever is smaller)	
12	Vibration	Appearance	No defects or abnormalities	
		Capacitance Change	Within the specified tolerance	
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.
		I.R.	More than 10,000M Ω or 500 Ω -F (*50 Ω -F) (Whichever is smaller)	
13	Resistance to Solder Heat	Appearance	No defects which may affect performance	
		Capacitance Change	Within the specified tolerance	
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.
		I.R.	More than 10,000M Ω or 500 Ω -F (*50 Ω -F) (Whichever is smaller)	
14	Thermal Shock	Appearance	No defects which may affect performance	
		Capacitance Change	Within $\pm 2.5\%$ or $\pm 0.25\text{pF}$ (Whichever is larger)	Within $\pm 15.0\%$
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.
		I.R.	More than 10,000M Ω or 500 Ω -F (*50 Ω -F) (Whichever is smaller)	

Per MIL-STD-202 Method 215

Three shocks in each direction should be applied along 3 mutually perpendicular axes of the test specimen (18 shocks)
 Test Pulse
 Wave form : Half-sine
 Duration : 0.5ms
 Peak value : 1,500G
 Velocity change : 4.7m/s

The specimens should be subjected to a simple harmonic motion having a total amplitude of 1.5mm. The entire frequency range of 10 to 2,000 Hz and return to 10 Hz should be traversed in 20 minutes. This cycle should be performed 12 times in each of three mutually perpendicular directions (total of 36 times).


Temperature (Eutectic solder solution) : $260 \pm 5^\circ\text{C}$
 Dipping Time : $10 \pm 1\text{s}$
 Let sit for 24 ± 2 hours at room temperature, then measure.
 Initial measurement
 Perform the initial measurement according to Note 1 for Class II.

Perform the 300 cycles according to the two heat treatments listed in the following table.
 Transfer Time : 20sec. max.


Step	1	2
Temp.($^\circ\text{C}$)	$-55+0/-3$	$125+3/-0$
Time(min.)	15 ± 3	15 ± 3

Initial measurement
 Perform the initial measurement according to Note 1 for Class II.

Specifications and Test Methods (For Automotive Application)

No.	AEC-Q200 Test Item		Specification		Test Methods and Conditions																		
			Class I	Class II																			
15	ESD	Appearance	No defects which may affect performance		Per AEC-Q200-002																		
		Capacitance Change	Within the specified tolerance																				
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.																			
		I.R.	More than 10,000MΩ or 500Ω·F (*50Ω·F) (Whichever is smaller)																				
16	Solderability		95% of the terminations is to be soldered evenly and continuously.		(a) Preheat at 155℃ for 4 hours, and then immerse the capacitor in a solution of ethanol and rosin. Immerse in eutectic solder solution for 5+0/-0.5 seconds at 235±5℃. (b) Steam aging for 8 hours, and then immerse the capacitor in a solution of ethanol and rosin. Immerse in eutectic solder solution for 5+0/-0.5 seconds at 235±5℃. (c) Steam aging for 8 hours, and then immerse the capacitor in a solution of ethanol and rosin. Immerse in eutectic solder solution for 120±5 seconds at 260±5℃.																		
17	Electrical Characterization	Appearance	No defects or abnormalities		The capacitance/Q/D.F. should be measured at 25℃ at the frequency and voltage shown in the table.																		
		Capacitance Change	Within the specified tolerance																				
		Q/D.F.	30pF min.: $Q \geq 1000$ 30pF max.: $Q \geq 400+20 \times C$ C: Nominal Capacitance (pF)	Rated Voltage 50V: 0.025 max. 25V: 0.03 max. 16V: 0.035 max. 10V: 0.05 max. *0.125 max.	<table><tr><th>Class</th><th>Capacitance (C)</th><th>Frequency</th><th>Voltage</th></tr><tr><td rowspan="2">Class I</td><td>C<1000pF</td><td>1±0.1MHz</td><td>0.5~5Vrms</td></tr><tr><td>C≥1000pF</td><td>1±0.1kHz</td><td>1±0.2Vrms</td></tr><tr><td rowspan="2">Class II</td><td>C≤10μF</td><td>1±0.1kHz</td><td>0.5~1.0Vrms</td></tr><tr><td>C>10μF</td><td>120±24Hz</td><td>0.5±0.1Vrms</td></tr></table> · Initial measurement Perform the initial measurement according to Note1 for Class II · Measurement after test Take it out and set it for 24±2 hours (Class II) then measure	Class	Capacitance (C)	Frequency	Voltage	Class I	C<1000pF	1±0.1MHz	0.5~5Vrms	C≥1000pF	1±0.1kHz	1±0.2Vrms	Class II	C≤10μF	1±0.1kHz	0.5~1.0Vrms	C>10μF	120±24Hz	0.5±0.1Vrms
		Class	Capacitance (C)	Frequency	Voltage																		
		Class I	C<1000pF	1±0.1MHz	0.5~5Vrms																		
			C≥1000pF	1±0.1kHz	1±0.2Vrms																		
Class II	C≤10μF	1±0.1kHz	0.5~1.0Vrms																				
	C>10μF	120±24Hz	0.5±0.1Vrms																				
I.R. at 25℃	More than 100,000MΩ or 1,000Ω·F (Whichever is smaller)	More than 10,000MΩ 500Ω·F (*50Ω·F) (Whichever is smaller)	Should be measured with a DC voltage not exceeding rated voltage at 25℃ and 125℃ for 2 minutes of charging.																				
I.R. at 125℃	More than 10,000MΩ or 100Ω·F (Whichever is smaller)	More than 1,000MΩ or 10Ω·F (*1Ω·F) (Whichever is smaller)																					
Voltage proof	No dielectric breakdown or mechanical breakdown																						
18	Board Flex	Appearance	No defects which may affect performance		Apply a force in the direction shown in the following figure for 60±5 seconds.  Flexure for Class I: 3mm max. for Class II: 3mm max. – Reflow soldering only																		
		Capacitance Change	Within ±5.0% or ±0.5pF (Whichever is larger)	Within the specified tolerance																			
19	Terminal Strength	Appearance	No defects which may affect performance		Apply 18N ¹⁾ force in parallel with the test jig for 60±1 seconds. ¹⁾ 10N for 1608(EIA:0603) size 2N for 1005(EIA:0402) size																		
		Capacitance Change	Within ±5.0% or ±0.5pF (Whichever is larger)	Within the specified tolerance																			

Specifications and Test Methods (For Automotive Application)

No.	AEC-Q200 Test Item		Specification		Test Methods and Conditions													
			Class I	Class II														
20	Beam Load		The chip endure following force. <table><tr><th>Chip Length</th><th>Thickness (T)</th><th>Force</th></tr><tr><td rowspan="2">2.5mm max.</td><td>T≤0.5mm</td><td>8N</td></tr><tr><td>T>0.5mm</td><td>20N</td></tr><tr><td rowspan="2">3.2mm min.</td><td>T<1.25mm</td><td>15N</td></tr><tr><td>T≥1.25</td><td>54.5N</td></tr></table>		Chip Length	Thickness (T)	Force	2.5mm max.	T≤0.5mm	8N	T>0.5mm	20N	3.2mm min.	T<1.25mm	15N	T≥1.25	54.5N	Apply a force as shown in the following figure. (i) Chip Length : 2.5mm max. (ii) Chip Length : 3.2mm min. Beam Speed : 0.5mm/s Beam Speed : 2.5mm/s 
Chip Length	Thickness (T)	Force																
2.5mm max.	T≤0.5mm	8N																
	T>0.5mm	20N																
3.2mm min.	T<1.25mm	15N																
	T≥1.25	54.5N																
21	Capacitance Temperature Characteris- tics	Capacitance Change		X7R : Within ±15% X7S : Within ±22% X6S : Within ±22% X7T : Within +22% ~ -33%	(i) Class I The temperature coefficient is determined using the capacitance measured in step 3 as a reference. When cycling the temperature sequentially from step 1 through 5, the capacitance should be within the specified tolerance for the temperature coefficient. The capacitance drift is calculated by dividing the differences between the maximum and minimum measured values in steps 1, 3 and 5 by the capacitance value in step 3. <table><tr><th>Step</th><td>1</td><td>2</td><td>3</td><td>4</td><td>5</td></tr><tr><th>Temp.(°C)</th><td>25±2</td><td>-55±3</td><td>25±2</td><td>125±3</td><td>25±2</td></tr></table> (ii) Class II The ranges of capacitance change compared with the 25℃ value over the temperature range from -55℃ to 125℃. Initial measurement Perform the initial measurement according to Note 1 for Class II.	Step	1	2	3	4	5	Temp.(°C)	25±2	-55±3	25±2	125±3	25±2	
		Step	1	2		3	4	5										
		Temp.(°C)	25±2	-55±3		25±2	125±3	25±2										
Temperature Coefficient	0±30 ppm/℃																	
Capacitance Drift	Within ±0.2% or ±0.05pF (Whichever is larger)																	

In the case of "" is specifications for "Thin Layer Large Capacitance Type"

Note 1. Initial Measurement for Class II

Perform a heat treatment at 150±0/-10°C for one hour, and then let sit for 24±2 hours at room temperature, then measure.

"Following the International standards, the title of each test item is subject to change."

Packing


(1) Bulk Packing

- ① 1000 pcs per polybag
- ② 5 polybags per inner box
- ③ 10 inner boxes per out box

(2) Reel Packing

- ① 8~10 reels per inner box
- ② 6 inner boxes per out box

(3) Reel Dimensions





(Unit : mm)

Mark	Size Code	EIA Code	A	B	C	D	E	W
7 " Reel	1005~3225	0402~1210	$\Phi 178 \pm 2$	$\Phi 50 \text{Min}$	$\Phi 13 \pm 0.5$	$\Phi 21 \pm 0.8$	2 ± 0.5	10 ± 1.5
	4520~4532	1808~1812	$\Phi 180 +0, -3$	$\Phi 60 -0, +1$	$\Phi 13 \pm 0.2$	$\Phi 57 -0 +1$	3 ± 0.2	13 ± 0.5
13 " Reel	1005~3225	0402~1210	$\Phi 330 \pm 2$	$\Phi 70 \text{Min}$	$\Phi 13 \pm 0.5$	$\Phi 21 \pm 0.8$	2 ± 0.5	10 ± 1.5


(4) Number of Package

Size Code	EIA Code	7"	13"
		Quantity(pcs)/Reel	Quantity(pcs)/Reel
1005	0402	10,000	50,000
1608	0603	4,000	15,000
2012	0805	3,000 ~ 4,000	8,000 ~ 15,000
3216	1206	2,000 ~ 4,000	6,000 ~ 10,000
3225	1210	1,000 ~ 3,000	4,000 ~ 10,000
4520	1808	1,500 ~ 3,000	—
4532	1812	500 ~ 1,000	1,500 ~ 5,000

(5) Tape Dimensions



Size Code	EIA Code	A	B	C	D	E	F	G	H	J
1005	0402	1.15 ± 0.1	0.65 ± 0.1	8.0 ± 0.3	3.5 ± 0.05	1.75 ± 0.1	2.0 ± 0.05	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
1608	0603	1.9 ± 0.2	1.10 ± 0.2	8.0 ± 0.3	3.5 ± 0.05	1.75 ± 0.1	4.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
2012	0805	2.4 ± 0.2	1.65 ± 0.2	8.0 ± 0.3	3.5 ± 0.05	1.75 ± 0.1	4.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
3216	1206	3.6 ± 0.2	2.00 ± 0.2	8.0 ± 0.3	3.5 ± 0.05	1.75 ± 0.1	4.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
3225	1210	3.6 ± 0.2	2.80 ± 0.2	8.0 ± 0.3	3.5 ± 0.05	1.75 ± 0.1	4.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
4520	1808	4.8 ± 0.2	2.3 ± 0.2	12.0 ± 0.3	5.5 ± 0.1	1.75 ± 0.1	4.0 ± 0.1 8.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1
4532	1812	4.9 ± 0.2	3.6 ± 0.2	12.0 ± 0.3	5.5 ± 0.1	1.75 ± 0.1	8.0 ± 0.1	2.0 ± 0.1	4.0 ± 0.1	1.5 ± 0.1



Caution

► Storage Condition

When solderability is considered, capacitor are recommended to be used in 12 months.

- (1) Temperature: $25^{\circ}\text{C} \pm 10^{\circ}\text{C}$
- (2) Relative Humidity: Below 70% RH

► The Regulation of Environmental Pollution Materials


Never use materials mentioned below in MLCC products regulated this document.

Pb, Cd, Hg, Cr^{+6} , PBB(Polybrominated biphenyl), PBDE(Polybrominated diphenyl ethers), asbestos

► Mounting Position


Choose a mounting position that minimizes the stress imposed on the chip during flexing or bending of the board.

[Component direction]



Locate chip horizontal to the direction in which stress acts.

[Chip Mounting Close to Board Separation Point]



Chip arrangement
Worst A-C- (B, D)
Best

► Reflow Soldering

- The sudden temperature change easily causes mechanical damages to ceramic components. Therefore, the preheating procedures should be required for the soldering of ceramic components.
- Please refer to the recommended soldering profiles as shown in figures, and keep the temperature difference(ΔT) within the range recommended in Table 1.


Table 1

Size code (EIA Code)	Temperature Difference
1005~3216 (0402~1206)	$\Delta T \leq 190^{\circ}\text{C}$
3225 (1210)	$\Delta T \leq 130^{\circ}\text{C}$


- Capacitors designated as for only reflow soldering must not apply to wave soldering.

Recommended Reflow Soldering Profile for Lead Free Solder

Infrared Reflow



Vapor Reflow



Note

- 'Aging'/'De-aging' behavior of high dielectric constant type MLCCs
(Typically represented by X7R temperature characteristic of which main composition is BaTiO₃)

'Aging' / 'De-aging' Behavior of high dielectric MLCCs Please note that high dielectric type dielectric ceramic capacitors have a "normal" 'aging' behavior / characteristic, that is; their capacitance value decreases with time from its value when it was first manufactured. From that date, the capacitance value begins to decrease at a logarithmic rate defined by:

$$C_t = C_{24} (1 - k \log_{10} t)$$


where,

C_t : Capacitance value, t hours after the start of 'aging'

C_{24} : Capacitance value, 24 hours after its manufacture

k : Aging constant (capacitance decrease per decade-hour)

t : time, in hours, from the start of 'aging'



The capacitance value can be restored (also known as 'de-aged') by exposing the component to elevated temperatures approaching its curie temperature (approximately 120°C). This 'de-aging' can occur during the component's solder-assembly onto the PCB, during life or temperature cycle testing, or by baking at 150°C for about 1 hour.